

# EUROPEAN PATENT OFFICE

## Patent Abstracts of Japan

PUBLICATION NUMBER : 63166736  
PUBLICATION DATE : 09-07-88  
  
APPLICATION DATE : 12-07-86  
APPLICATION NUMBER : 61164500



APPLICANT : SUMITA KOGAKU GLASS SEIZOSHO:KK;

INVENTOR : NAGAHAMA SHINOBU;

INT.CL. : C03C 10/04 // C03C 3/095 C03C 4/04

TITLE : PHOTSENSITIVE CRYSTALLIZED GLASS HAVING LOW EXPANSION COEFFICIENT

ABSTRACT : PURPOSE: To provide a crystallized glass composed of a specific glass composition, having high meltability of the glass and excellent chemical machinability, i.e. large crystallization temperature difference between a part irradiated with ultraviolet ray and a non-irradiated part and giving a crystallized final product having a specific thermal expansion coefficient.

CONSTITUTION: The objective glass is composed of 55~70wt.% SiO<sub>2</sub>, 8~12% Li<sub>2</sub>O, 12~20% Al<sub>2</sub>O<sub>3</sub>, 0~3% Na<sub>2</sub>O, 2~5% K<sub>2</sub>O, 0~2% Cs<sub>2</sub>O, 1~3% BaO and 0~4% ZnO and containing 0.001~0.03% CeO<sub>2</sub> and 0.05~0.1% Ag or 0.0005~0.02% Au as photosensitive components. The glass is sensitive to ultraviolet ray to effect the selective crystallization of the ultraviolet irradiated part by the heat-treatment at 500~600°C. The crystallized product produced by the heat-treatment at 800~900°C to precipitate fine crystals in the glass has a thermal expansion coefficient of 40~70×10<sup>-7</sup>/°C.

COPYRIGHT: (C)1988,JPO&Japio